



# TEST REPORT

US BUTTON / EMSIG MFG  
 328 KENNEDY DRIVE  
 PUTNAM, CT 06260

ATTN: BURT ELLIOTT

LAB NO.: (6508)351-0116 Addendum  
 FORM NO.: N/L  
 DATE IN: DECEMBER 16, 2008  
 MODIFIED DATE IN: N/A  
 DATE OUT: DECEMBER 29, 2008  
 ADDENDUM DATE OUT: JANUARY 8, 2009  
 DIVISION: N/L  
 DEPARTMENT: N/L  
 CATEGORY: N/L  
 BUYER: N/L  
 NO. OF WORKING DAYS: 7  
 PAGE: PAGE 1 OF 3

OVERALL RATING	
PASS	_____ X _____
FAIL	_____
DATA	_____

<b>Vendor:</b>	US Button	<b>Agent:</b>	N/L
<b>Fabric Supplier/Mill:</b>	N/L	<b>Factory/Manufacturer:</b>	US Button Corp
<b>P.O. No.:</b>	N/L	<b>Style No.:</b>	30 Industro
<b>Sample Description:</b>	Plastic Button	<b>Style Description:</b>	N/L
<b>Color:</b>	N/L (Grey)	<b>Country of Origin:</b>	N/L
<b>Claimed Fabric Weight:</b>	N/L	<b>Claimed Fabric Count:</b>	N/L
<b>Yarn Size:</b>	N/L	<b>Submitted Size:</b>	N/L
<b>Size Range:</b>	N/L	<b>FPU No.:</b>	N/L
<b>GPU No.:</b>	N/L	<b>End Use:</b>	Clothing

<b>Product Category:</b>	Trims
<b>Test Requested:</b>	Formaldehyde (AATCC 112 & JIS L 1041), Lead in Substrates
<b>Previous Report No.:</b>	N/L

<b>Submitted Fiber Content:</b>	Melamine
<b>Actual Fiber Content:</b>	N/R
<b>Suggested Fiber Content:</b>	N/A
<b>Submitted Care Instruction(s):</b>	N/L
<b>Client Expected Care Instruction:</b>	N/L
<b>Suggested Care Instruction(s):</b>	N/R



TEST PROPERTY	PASS	FAIL	DATA	
FORMALDEHYDE (AATCC 112)			X	
FORMALDEHYDE (JIS L 1041)			X	
LEAD IN SUBSTRATES	X			

An Addendum was issued on January 8, 2009 in order to add the JIS L 1041 Method of Formaldehyde testing.

Client Specialist  
Michael Medeiros

For any **Administrative** questions please contact:  
Kristen Miro  
508-844-2717  
[kristen.miro@us.bureauveritas.com](mailto:kristen.miro@us.bureauveritas.com)

For any **Technical** questions please contact:  
Cathy Rodrigues  
508-844-2742  
[cathy.rodrigues@us.bureauveritas.com](mailto:cathy.rodrigues@us.bureauveritas.com)

For any **Analytical** questions please contact:  
John Gerringe  
508-844-2979  
[john.gerringe@us.bureauveritas.com](mailto:john.gerringe@us.bureauveritas.com)



<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
<u>FORMALDEHYDE</u> (AATCC 112)		
(PPM)	100.6	-
<u>FORMALDEHYDE</u> (JIS L 1041)		
(PPM)	< 20	-
<u>LEAD IN SUBSTRATES</u> (EPA 3050B MOD/3051A MOD)		
(PPM)	< 50	≤ 600

**KEYS:**

- N/A: Not Applicable
- N/R: Not Requested
- N/L: Not Listed
- I/S: Insufficient Sample