

Recycled Ecological Buttons

A2016 A2017	<p>The Recycled Paper material contains 45-55% of recycled paper, 28-40% of fillers (recycled thermosetting) and 7-15% of technical binders and dyers. In conformity With Oeko-Tex*</p> <p>Resistance to washing: $T_{max} = 104^{\circ} F$ Resistance to ironing: $T_{max} = 240^{\circ} F$</p>
A1872	<p>The Canapa material contains 50-60% of recycled hemp fibers, 15-20% of fillers (recycled thermosetting) and 15-20% of technical binders and dyers. The material is in conformity with Oeko-Tex.* Hemp is an 8,000 year old vegetable. It's rough endless fibers are considered highly ecological as they do not need pesticides when growing in big plantations.</p> <p>Resistance to washing: $T_{max} = 104^{\circ} F$ Resistance to ironing: $T_{max} = 240^{\circ} F$</p>
A1870 A1871	<p>The Ecovelvet material contains 70-80% of cotton fibers, 2-5% of plasticizers and dyers and 15-30% of technical binders. The material is in conformity with Oeko-Tex*</p> <p>Resistance to washing: $T_{max} = 104^{\circ} F$ Resistance to ironing: $T_{max} = 240^{\circ} F$</p>
A1873	<p>The Bruse material contains 50-60% of begetable and biodegradable fibers, 30% of fillers (recycled thermosetting) and 20% of technical binders and dyers. In conformity with Oeko-Tex*</p> <p>Resistance to washing: $T_{max} = 104^{\circ} F$ Resistance to ironing: $T_{max} = 240^{\circ} F$</p>
	<p>The Ecocoroza material contains corozo recycled powder (about 20%). The material is in conformity with Oeko-Tex Certificate.</p>
A1869	<p>The WOOD material contains 35-45% of recycled wood pulp – wood saw dust and biodegradable wood fibres. 15% recycled thermosetting and 50% recycled polyester. In conformity with Oeko-Tex*</p>

*Oeko-Tex Standard

The Oeko-Tex Standard 100 has been developed by a European group of textile institutes as testing program to screen for the presence of certain hazardous elements and compounds within consumer textiles.